

PRODUCT CHARACTERISTICS

FORMAT	Lillehammer		
Width	212	mm	
Length	1380	mm	
Number of panels per pack	7		
m² per pack	2,048	m ²	
Bevels	with pressed bevel around the plank		
Thickness	9,0	mm	
Tongue and groove	Uniclic		
Water resistance warranty	15	years	
	72	hours	(stagnating water)

PANEL BUILD UP



1. Superior wear and scratch-resistance layer
2. Crystal-clear decor
3. Moisture-resistant HDF core
4. Back stabiliser

FACTORY WARRANTY

	METHOD	PARAMETERS	
Usage class	EN ISO 10874	Class	21-22-23/31-32
CE	EN 14041:2004+AC:2005+AC:2006	Notified body	NB 0493 - Centexbel
UKCA	EN 14041:2004+AC:2005+AC:2006	Approved Body	AB 8515 - Centexbel
Warranty	Residential use	See warranty conditions	Lifetime
	Commercial use	See warranty conditions	Water resistancy 15 years 5 years 5 years

GENERAL DATA (ACCORDING TO EN 13329)

	METHOD	PARAMETERS	NORM REQUIREMENTS
Abrasion resistance	ISO 24338 - Prodecure A		≥ 4000 cycles
Abrasion class	EN 13329		AC4
Impact resistance	EN 17368	Small ball	≥ 35 mm
	EN 13329	Big ball	≥ 600 mm
Scratch resistance	EN 438-2, 25		Charge ≥ 3N
Effect of a castor chair	EN ISO 4918 (with underlay)	Type W (EN 12529)	15000 cycles
Thickness swelling	ISO 24336	after 24h immersion at 20°C	≤ 18%
Locking strength	ISO 24334	F10,2 long side Fmax long side Fs0,2 short side Fmax short side	≥ 1 kN/m ≥ 2 kN/m
Effect of a furniture leg	EN ISO 16581		No damage shall be visible, when tested with foot type 0
Surface soundness	EN 13329	N/mm ²	≥ 1,25
Static Indentation	EN ISO 24343-1		Residual indentation ≤ 0,05 mm
Resistance to staining	EN 438-2	Group 1, 2 Group 3	Class 5 Class 4
General appearance	EN 13329	Height differences Opening between joints Cupping in the length Cupping in the width	≤ 0,15 mm ≤ 0,20 mm concave ≤ 0,50% convex ≤ 1,00% concave ≤ 0,15% convex ≤ 0,20%
Dimensional variations after changes in relative humidity	EN 13329	δl δw	δl average ≤ 0,9 mm δw average ≤ 0,9 mm
Light fastness	EN ISO 4892-2:2013 procedure B - cycle 2 or cycle 5	Grey reference	Class ≥ 4

GENERAL DATA (ACCORDING TO EN 13329)

	METHOD	PARAMETERS	NORM REQUIREMENTS	PERGO VALUES
Water resistance	ISO 4760	Qualitative rating for Recovery swell	< 3	1
		Quantitative rating for Recovery swell	≤0,3mm	≤0,03mm
		Joint leakage	No requirement	No leakage

ENVIRONMENT, SAFETY & HEALTH

	METHOD	PARAMETERS		
Impact sound reduction	ISO 712/2	On a PERGO underlay		ΔL _w ≈ 18dB (Depending on used underlay)
Floor heating		On a PERGO underlay	See special instructions	Suitable
Formaldehyde emission	EN 717-1	ppm		< E0,5
Anti-static	EN 1815			≤ 2,0 kV
Reaction to fire	EN 13501-1	Class		Bfl-s1 (with all Pergo underlays)
Thermal resistance	EN 12667	m ² K/W		0,059 m ² K/W
Slip resistance	EN 13893	μ		DS: μ ≥ 0,30

CERTIFICATES

EU Ecolabel	SE/035/001
AFFSET	A+
PEFC	PEFC/07-32-37
M1	
Nordic Ecolabel	30290001
EPD	



EN 13841:2004 / AC:2006
Laminated floor coverings
EN 13329:2023



EN 13841:2004 / AC:2006
Laminated floor coverings
EN 13329:2023

